

NOMINAL THICKNESS FOR STANDARD PRESSURE CLASSES OF DUCTILE IRON PIPE



For Generations

Size In.	Outside Diameter In.	Pressure Class*				
		150	200	250	300	350
Normal Thickness — in.						
3	3.96	—	—	—	—	0.25**
4	4.80	—	—	—	—	0.25**
6	6.90	—	—	—	—	0.25**
8	9.05	—	—	—	—	0.25**
10	11.10	—	—	—	—	0.26
12	13.20	—	—	—	—	0.28
14	15.30	—	—	0.28	0.30	0.31
16	17.40	—	—	0.30	0.32	0.34
18	19.5	—	—	0.31	0.34	0.36
20	21.60	—	—	0.33	0.36	0.38
24	25.80	—	0.33	0.37	0.40	0.43
30	32.00	0.34	0.38	0.42	0.45	0.49
36	38.30	0.38	0.42	0.47	0.51	0.56

* Pressure Classes are defined as the rated water pressure of the pipe in psi. The thicknesses shown are adequate for the rated water working pressure plus a surge allowance of 100 psi. Calculations are based on a minimum yield strength of 42,000 and a 2.0 safety factor times the sum of the working pressure and 100 psi surge allowance.

** Calculated thicknesses for these sizes and pressure ratings are less than those shown above. Presently, these are the lowest nominal thicknesses available in these sizes.

NOTE: Per ANSI/AWWA C150/A21.50 the thicknesses above include the 0.08 in. service allowance and the casting tolerance listed below by size ranges:

SIZE (Inches)	CASTING TOLERANCES (Inches)
3–8	-0.05
10–12	-0.06
14–36	-0.07



IRON STRONG



Canada Pipe Company ULC

NEW JERSEY
183 Sitgreaves St.
Phillipsburg, NJ 08865
908-454-1161
mcwaneductile.com

OHIO
2266 S. 6th St.
Coshocton, OH 43812
740-622-6651
mcwaneductile.com

UTAH
1401 E 2000 S.
Provo, UT 84603
801-373-6910
mcwaneductile.com

CANADA
1757 Burlington St. E
Hamilton, ON L8N-3R5
905-547-3251
canadapipe.com

